LVT DRYBACK | 3.0 MM TOTAL THICKNESS | 0.55 MM WEAR LAYER | 184.15 × 1219.2 MM

PREMIUM • SKU EF-DB-PRE30-055-1842X12192 • CLASS 34 / COMMERCIAL

Prepared by Ecoflors Technical Team • Version 2026.11.05-R01 • ecoflors.com

PRODUCT CONFIGURATION		PACKING & LOADING • ESTIMATED	
Product type	LVT Dryback Plank Flooring	**Carton packing**	18 pcs/carton
Application	Commercial	**Carton dimensions**	192.15 × 1229.2 × 56 mm (7.56 × 48.39 × 2.20 in)
Product format	Straight plank	**Carton coverage**	4.041 m²/carton (43.50 sq ft/carton)
Dimensions	184.15 × 1219.2 mm (7.25 × 48.00 in)	**Estimated carton net weight**	23.04 kg/carton (50.78 lb/carton)
Total thickness	3.0 mm	**Estimated carton gross weight**	23.54 kg/carton (51.89 lb/carton)
Wear layer	0.55 mm (≈22 mil)	**Pallet packing**	50 cartons/pallet
Construction	UV coating + wear layer + décor film + LVT middle and bottom layers; no fiberglass layer	**Pallet layout**	5 cartons/layer × 10 layers
Surface texture	Natural wood-grain texture	**Pallet coverage**	202.064 m²/pallet (2,175.00 sq ft/pallet)
Surface treatment	UV-cured matte finish (gloss level: 4–6 GU)	**Loaded pallet dimensions**	980 × 1240 × 695.0 mm (38.58 × 48.82 × 27.36 in)
Installation method	Glue-down installation	**Estimated pallet net weight**	1,151.77 kg/pallet (2,539.21 lb/pallet)
Bevel	4-sided micro bevel	**Estimated pallet gross weight**	1,191.77 kg/pallet (2,627.39 lb/pallet)
Classification	Class 34 — also suitable for Class 33 applications	**20 ft GP loading**	20 pallets/20 ft GP (up to 3-high stacking)
Residential service life	15+ years	**20 ft GP coverage**	4041.282 m²/20 ft GP (43,500.00 sq ft/20 ft GP)
Product series	Premium	**20 ft GP cargo gross weight**	23,835.31 kg/20 ft GP (52,547.86 lb/20 ft GP)

LVT DRYBACK PLANK FLOORING — TECHNICAL PERFORMANCE

CHARACTERISTIC	TEST STANDARD	REFERENCE VALUE
Overall thickness	ISO 24346:2006	3.0 mm
Density	ISO 23996:2007	1.75–1.90 g/cm³
Wear layer thickness	ISO 24340:2006	0.55 mm (≈22 mil)
Classification	ISO 10874:2009	Class 34 — also suitable for Class 33 applications
Micro-scratch resistance	EN 16094	MSR-B2
Dimensional tolerance	ISO 24342:2007	Length / width: max. ±0.50 mm
Squareness	ISO 24342:2007	Max. ≤ 0.20 mm
Straightness	ISO 24342:2007	Max. ≤ 0.20 mm
Dimensional stability	ISO 23999:2021	≤ 0.12%
Curling	ISO 23999:2021	≤ 1.2 mm
Residual indentation	ISO 24343-1:2007	≤ 0.10 mm
Light stability	ISO 105-B02, Method 3	> Grade 6
Reaction to fire	EN 13501-1	Bfl-s1
Dry slip resistance	EN 13893	Class DS
Ramp slip resistance	DIN 51130	R10
Wear resistance	EN 660-2	Group P
Peel resistance	ISO 24345:2006	> 75 N/50 mm
Resistance to stains / chemicals	ISO 26987:2008	No change in surface dulling, surface attack or staining detected
Flexibility	ISO 24344:2008, Method A	No cracking in either direction with a 50 mm mandrel
Castor chair	ISO 4918:2016	After 25,000 cycles: no visible damage
Soluble heavy metals	ASTM F963-11	Not detected
Formaldehyde emission	EN 717-1:2004	Not detected
Utilization / recyclability	—	Recyclable