LVT LOOSE LAY | 4.0 MM TOTAL THICKNESS | 0.30 MM WEAR LAYER | 184.15 × 1219.2 MM

ESSENTIAL • SKU EF-LL-ESS40-030-1842X12192 • RESIDENTIAL • CLASS 23

Prepared by Ecoflors Technical Team • Version 2026.11.04-R01 • ecoflors.com

PRODUCT CONFIGURATION		PACKING & LOADING • ESTIMATED	
Product type	LVT Loose Lay Plank Flooring	**Carton packing**	13 pcs/carton
Application	Residential	**Carton dimensions**	192.2 × 1229.2 × 54.0 mm (7.56 × 48.39 × 2.13 in)
Product format	Straight plank	**Carton coverage**	2.918 m²/carton (31.42 sq ft/carton)
Dimensions	184.15 × 1219.2 mm (7.25 × 48.00 in)	**Estimated carton net weight**	22.18 kg/carton (48.90 lb/carton)
Total thickness	4.0 mm	**Estimated carton gross weight**	22.68 kg/carton (50.01 lb/carton)
Backing / underlay	Anti-skid backing; no attached pad	**Pallet packing**	50 cartons/pallet
Wear layer	0.30 mm (≈12 mil)	**Pallet layout**	5 cartons/layer × 10 layers
Construction	UV coating + wear layer + décor film + LVT reinforced layer with fiberglass + anti-skid backing; dual fiberglass reinforcement available	**Pallet coverage**	145.935 m²/pallet (1570.83 sq ft/pallet)
Surface texture options	Natural wood-grain texture, EIR (embossed-in-register) or crystal embossing	**Loaded pallet dimensions**	980 × 1240 × 675.0 mm (38.58 × 48.82 × 26.57 in)
Surface treatment	UV-cured matte finish (gloss level: 4–6 GU)	**Estimated pallet net weight**	1109.11 kg/pallet (2445.16 lb/pallet)
Installation method	Loose-lay installation	**Estimated pallet gross weight**	1149.11 kg/pallet (2533.35 lb/pallet)
Bevel	4-sided micro bevel	**20 ft GP loading**	21 pallets/20 ft GP (up to 3-high stacking)
Indicative use class	Class 23	**20 ft GP coverage**	3064.639 m²/20 ft GP (32987.50 sq ft/20 ft GP)
Residential service life	25+ years	**20 ft GP cargo gross weight**	24,131.26 kg/20 ft GP (53,200.31 lb/20 ft GP)

LVT LOOSE LAY FLOORING — TECHNICAL PERFORMANCE

CHARACTERISTIC	TEST STANDARD	REFERENCE VALUE
Overall thickness	ISO 24346:2006	4.0 mm
Density	ISO 23996:2007	1.80–1.90 g/cm³
Wear layer thickness	ISO 24340:2006	0.30 mm (≈12 mil)
Indicative use class	ISO 10874:2009	Class 23
Micro-scratch resistance	EN 16094	MSR-B2
Dimensional tolerance	ISO 24342:2007	Length / width: max. ±0.50 mm
Squareness	ISO 24342:2007	Max. ≤ 0.20 mm
Straightness	ISO 24342:2007	Max. ≤ 0.20 mm
Dimensional stability	ISO 23999:2021	≤ 0.12%
Curling	ISO 23999:2021	≤ 1.0 mm
Residual indentation	ISO 24343-1:2007	≤ 0.10 mm
Light stability	ISO 105-B02, Method 3	> Grade 6
Reaction to fire	EN 13501-1	Bfl-s1
Dry slip resistance	EN 13893	Class DS
Ramp slip resistance	DIN 51130	R10
Wear resistance	EN 660-2	Group P
Peel resistance	ISO 24345:2006	> 75 N/50 mm
Resistance to stains / chemicals	ISO 26987:2008	No change in surface dulling, surface attack or staining detected
Flexibility	ISO 24344:2008, Method A	No cracking in either direction with a 50 mm mandrel
Castor chair	ISO 4918:2016	After 25,000 cycles: no visible damage
Soluble heavy metals	ASTM F963-11	Not detected
Formaldehyde emission	EN 717-1:2004	Not detected
Utilization / recyclability	—	Recyclable