ABA / RSVT HYBRID CLICK TILE FLOORING | 7.0 MM | 0.55 MM WEAR LAYER | 457.2 × 914.4 MM

PREMIUM • SKU EF-TABA-PRE7-055-4572X9144 • COMMERCIAL • CLASS 33

Prepared by Ecoflors Technical Team • Version 2026.11.05-R01 • ecoflors.com

PRODUCT CONFIGURATION		PACKING & LOADING	
Product type	ABA / RSVT Hybrid Click Tile Flooring	**Carton packing**	4 pcs/carton
Application	Commercial	**Carton dimensions**	469.2 × 929.4 × 30 mm (18.47 × 36.59 × 1.18 in)
Product format	Rectangular tile	**Carton coverage**	1.672 m²/carton (18.00 sq ft/carton)
Dimensions	457.2 × 914.4 mm (18.00 × 36.00 in)	**Carton net weight**	20.28 kg/carton (44.70 lb/carton)
Total thickness	7.0 mm	**Carton gross weight**	20.78 kg/carton (45.80 lb/carton)
Attached underlay	1.0 mm attached IXPE (7.5×)	**Pallet packing**	38 cartons/pallet
Wear layer	0.55 mm (≈22 mil)	**Pallet layout**	2 cartons/layer × 19 layers (2 × 1 layout)
Construction	6 mm ABA panel (LVT / SPC / LVT) + 1.0 mm IXPE	**Pallet coverage**	63.545 m²/pallet (684.00 sq ft/pallet)
Surface texture options	Stone or carpet texture options	**Loaded pallet dimensions**	960 × 940 × 705 mm (37.80 × 37.01 × 27.76 in)
Surface treatment	UV-cured matte finish (gloss level: 4–6 GU)	**Pallet net weight**	770.49 kg/pallet (1,698.64 lb/pallet)
Installation / click options	Floating installation • Uniclic, i4F or G2 options; confirmed per order	**Pallet gross weight**	810.49 kg/pallet (1,786.83 lb/pallet)
Bevel options	4-sided micro bevel or printed V-bevel options	**20 ft GP loading**	30 pallets/20 ft GP (up to 3-high stacking)
Indicative use class	Class 33	**20 ft GP coverage**	1906.370 m²/20 ft GP (20,520.00 sq ft/20 ft GP)
Commercial service life	15+ years	**20 ft GP cargo gross weight**	24,314.74 kg/20 ft GP (53,604.83 lb/20 ft GP)

ABA / RSVT HYBRID CLICK TILE FLOORING — TECHNICAL PERFORMANCE

CHARACTERISTIC	TEST STANDARD	REFERENCE VALUE
Overall thickness	ISO 24346	7 mm
Wear layer thickness	ISO 24340	0.55 mm (≈22 mil)
Indicative use class	ISO 10874	Class 33
Micro-scratch resistance	EN 16094	MSR-B2
Dimensional stability	ISO 23999:2021	≤ 0.12%
Curling	ISO 23999:2021	≤ 1.0 mm
Residual indentation	ISO 24343-1:2007	≤ 0.10 mm
Light stability	ISO 105-B02, Method 3	> Grade 6
Dry slip resistance	EN 13893	Class DS
Ramp slip resistance	DIN 51130	R10
Wear resistance	EN 660-2	Group P
Peel resistance	ISO 24345:2006	> 75 N/50 mm
Resistance to stains / chemicals	ISO 26987:2008	No change in surface dulling, surface attack or staining detected
Castor chair	ISO 4918:2016	After 25,000 cycles: no visible damage
Soluble heavy metals	ASTM F963-11	Not detected
Formaldehyde emission	EN 717-1:2004	Not detected