LVT DRYBACK TILE FLOORING | 2.5 MM | 0.50 MM WEAR LAYER | 457.2 × 609.6 MM

SELECT • SKU EF-TDB-SEL25-050-4572X6096 • RESIDENTIAL • CLASS 32

Prepared by Ecoflors Technical Team • Version 2026.11.05-R01 • ecoflors.com

PRODUCT CONFIGURATION		PACKING & LOADING	
Product type	LVT Dryback Tile Flooring	**Carton packing**	17 pcs/carton
Application	Residential	**Carton dimensions**	465.2 × 619.6 × 44.5 mm (18.31 × 24.39 × 1.75 in)
Product format	Rectangular tile	**Carton coverage**	4.738 m²/carton (51.00 sq ft/carton)
Dimensions	457.2 × 609.6 mm (18.00 × 24.00 in)	**Carton net weight**	22.51 kg/carton (49.62 lb/carton)
Total thickness	2.5 mm	**Carton gross weight**	23.01 kg/carton (50.72 lb/carton)
Attached underlay	None — no attached pad	**Pallet packing**	48 cartons/pallet
Wear layer	0.50 mm (≈20 mil)	**Pallet layout**	4 cartons/layer × 12 layers (2 × 2 layout)
Construction	UV coating + wear layer + décor film + LVT middle and bottom layers; no fiberglass	**Pallet coverage**	227.426 m²/pallet (2,448.00 sq ft/pallet)
Surface texture options	Stone or carpet texture options	**Loaded pallet dimensions**	950 × 1250 × 669 mm (37.40 × 49.21 × 26.34 in)
Surface treatment	UV-cured matte finish (gloss level: 4–6 GU)	**Pallet net weight**	1,080.28 kg/pallet (2,381.60 lb/pallet)
Installation / click options	Glue-down installation • No click system	**Pallet gross weight**	1,120.28 kg/pallet (2,469.79 lb/pallet)
Bevel options	4-sided micro bevel	**20 ft GP loading**	22 pallets/20 ft GP (up to 3-high stacking)
Indicative use class	Class 32	**20 ft GP coverage**	5003.386 m²/20 ft GP (53,856.00 sq ft/20 ft GP)
Residential service life	25+ years	**20 ft GP cargo gross weight**	24,646.08 kg/20 ft GP (54,335.31 lb/20 ft GP)

LVT DRYBACK TILE FLOORING — TECHNICAL PERFORMANCE

CHARACTERISTIC	TEST STANDARD	REFERENCE VALUE
Overall thickness	ISO 24346	2.5 mm
Wear layer thickness	ISO 24340	0.50 mm (≈20 mil)
Indicative use class	ISO 10874	Class 32
Micro-scratch resistance	EN 16094	MSR-B2
Dimensional stability	ISO 23999:2021	≤ 0.12%
Curling	ISO 23999:2021	≤ 1.2 mm
Residual indentation	ISO 24343-1:2007	≤ 0.10 mm
Light stability	ISO 105-B02, Method 3	> Grade 6
Dry slip resistance	EN 13893	Class DS
Ramp slip resistance	DIN 51130	R10
Wear resistance	EN 660-2	Group P
Peel resistance	ISO 24345:2006	> 75 N/50 mm
Resistance to stains / chemicals	ISO 26987:2008	No change in surface dulling, surface attack or staining detected
Castor chair	ISO 4918:2016	After 25,000 cycles: no visible damage
Soluble heavy metals	ASTM F963-11	Not detected
Formaldehyde emission	EN 717-1:2004	Not detected