LVT LOOSE LAY TILE FLOORING | 4.5 MM | 0.50 MM WEAR LAYER | 457.2 × 914.4 MM

SELECT • SKU EF-TLL-SEL45-050-4572X9144 • RESIDENTIAL • CLASS 23

Prepared by Ecoflors Technical Team • Version 2026.11.05-R01 • ecoflors.com

PRODUCT CONFIGURATION		PACKING & LOADING	
Product type	LVT Loose Lay Tile Flooring	**Carton packing**	6 pcs/carton
Application	Residential	**Carton dimensions**	465.2 × 924.4 × 29 mm (18.31 × 36.39 × 1.14 in)
Product format	Rectangular tile	**Carton coverage**	2.508 m²/carton (27.00 sq ft/carton)
Dimensions	457.2 × 914.4 mm (18.00 × 36.00 in)	**Carton net weight**	21.45 kg/carton (47.28 lb/carton)
Total thickness	4.5 mm	**Carton gross weight**	21.95 kg/carton (48.38 lb/carton)
Attached underlay	None — no attached pad	**Pallet packing**	38 cartons/pallet
Wear layer	0.50 mm (≈20 mil)	**Pallet layout**	2 cartons/layer × 19 layers (2 × 1 layout)
Construction	UV coating + wear layer + décor film + reinforced LVT core with fiberglass + anti-skid backing	**Pallet coverage**	95.318 m²/pallet (1,026.00 sq ft/pallet)
Surface texture options	Stone or carpet texture options	**Loaded pallet dimensions**	950 × 940 × 686 mm (37.40 × 37.01 × 27.01 in)
Surface treatment	UV-cured matte finish (gloss level: 4–6 GU)	**Pallet net weight**	814.97 kg/pallet (1,796.71 lb/pallet)
Installation / click options	Loose-lay installation • No click system	**Pallet gross weight**	854.97 kg/pallet (1,884.89 lb/pallet)
Bevel options	4-sided micro bevel	**20 ft GP loading**	29 pallets/20 ft GP (up to 3-high stacking)
Indicative use class	Class 23	**20 ft GP coverage**	2764.237 m²/20 ft GP (29,754.00 sq ft/20 ft GP)
Residential service life	25+ years	**20 ft GP cargo gross weight**	24,794.23 kg/20 ft GP (54,661.91 lb/20 ft GP)

LVT LOOSE LAY TILE FLOORING — TECHNICAL PERFORMANCE

CHARACTERISTIC	TEST STANDARD	REFERENCE VALUE
Overall thickness	ISO 24346	4.5 mm
Wear layer thickness	ISO 24340	0.50 mm (≈20 mil)
Indicative use class	ISO 10874	Class 23
Micro-scratch resistance	EN 16094	MSR-B2
Dimensional stability	ISO 23999:2021	≤ 0.12%
Curling	ISO 23999:2021	≤ 1.0 mm
Residual indentation	ISO 24343-1:2007	≤ 0.10 mm
Light stability	ISO 105-B02, Method 3	> Grade 6
Dry slip resistance	EN 13893	Class DS
Ramp slip resistance	DIN 51130	R10
Wear resistance	EN 660-2	Group P
Peel resistance	ISO 24345:2006	> 75 N/50 mm
Resistance to stains / chemicals	ISO 26987:2008	No change in surface dulling, surface attack or staining detected
Castor chair	ISO 4918:2016	After 25,000 cycles: no visible damage
Soluble heavy metals	ASTM F963-11	Not detected
Formaldehyde emission	EN 717-1:2004	Not detected